

Parama sintetica CK

Specificatii tehnice

Material: polipropilena si poliester

Standard: EN 919; EN 10556

Construcie: 3 fire rasucite / 8 fire impletite (4x2)

Utilizari: acostare, remorcare, pescuit industrial

Certificari: Lloyd`s Register si GL



Parama sintetica CK – 3 fire rasucite

Diametru (mm)	Greutate (g/m)	Rezistenta (kg)	Rezistenta (kN)
4	8	420	4,10
6	18	870	8,50
8	32	1490	14,6
10	50	2290	22,5
12	72	3240	31,8
14	98	4330	42,5
16	128	5540	54,4
18	162	6940	68,1
20	200	8440	82,8
22	240	10080	98,9
24	286	11820	116
26	336	13630	133,8
28	391	15670	153,8
30	446	17840	175
32	506	20010	196,3

Parama sintetica CK – 8 fire impletite (4x2)			
Diametru (mm)	Greutate (g/m)	Rezistenta (kg)	Rezistenta (kN)
36	644	26225	247,3
40	792	33520	328,8
44	968	40000	392,4
48	1144	47090	462
52	1342	54800	537,6
56	1562	62870	616,8
60	1793	71310	699,6
64	2035	80370	788,4
68	2310	90150	884,4
72	2574	100310	984
76	2882	111070	1089,6
80	3190	121710	1194
88	3861	145570	1428
96	4587	171250	1680

Densitate	1,004 g/cm³
Flotabilitate	DA
Temperatura maxima	120 °C
Rezistenta UV	excelenta
Rezistenta la acizi	foarte buna
Rezistenta la baze	foarte buna
Rezistenta la solventi organici	foarte buna